

DESCRIPTION

ORGANIC LIGHT-EMITTING DEVICE

5 TECHNICAL FIELD

The present invention relates to an organic light-emitting device, particularly to a device that emits light with the aid of the application of an electric field to a thin film comprised of an organic compound.

BACKGROUND ART

An organic light-emitting device is a device in which a thin film containing a fluorescent organic compound is sandwiched between an anode and a cathode. In the device produces, an exciton of the fluorescent compound is produced by injecting an electron or a hole from each of the electrodes and the light radiated when the exciton returns to the ground state is utilized.

In a research by Eastman Kodak Company in 1987 (Appl. Phys. Lett. 51, 913 (1987)), there is reported a light emission of about 1,000 cd/m² at an applied voltage of about 10 V for a device of separated-function two-layered structure using ITO for anode, a magnesium-silver alloy for cathode, respectively, an aluminum-quinolinol complex as an electron-

BEST AVAILABLE COPY

transporting material, and a light-emitting material
and a triphenylamine derivative as a hole
transporting material. Related patents include U.S.
Patent No. 4,539,507; U.S. Patent No. 4,720,432 and
5 U.S. Patent No. 4,885,211.

Light-emission from ultraviolet to infrared is
possible by changing a kind of the fluorescent
organic compounds and researches of various compounds
therefor have been conducted actively recently. For
10 example, they are described in U.S. Patent No.
5,151,629; U.S. Patent No. 5,409,783; U.S. Patent No.
5,382,477; Japanese Patent Application Laid-Open No.
H02-247278; Japanese Patent Application Laid-Open No.
H03-255190; Japanese Patent Application Laid-Open No.
15 H05-202356; Japanese Patent Application Laid-Open No.
H09-202878 and Japanese Patent Application Laid-Open
No. H09-227576.

Besides other than the organic light-emitting
device using monomeric materials as described above,
20 an organic light-emitting device using a conjugated
polymer has been reported by a group of Cambridge
University (Nature 347, 539 (1990)). In this report,
the light-emission in a monolayer by forming a film
of polyphenylenevinylene in a coating system is
25 confirmed. The related patents on organic light-
emitting devices using conjugated polymers include
U.S. Patent No. 5,247,190; U.S. Patent No. 5,514,878;

U.S. Patent No. 5,672,678; Japanese Patent Application Laid-Open No. H04-145192 and Japanese Patent Application Laid-Open No. H05-247460.

Thus, recent progress in organic light-emitting devices is remarkable, and possibilities for a wide range of applications are indicated since it is characterized in that a thin and light-weight light-emitting device having high luminance at a low applied-voltage, diversity of light-emitting wavelength and high-speed response can be prepared.

However, there are numbers of problems in terms of durability such as the variation with time during use for a long period of time and the deterioration due to an atmospheric gas containing oxygen or humidity. Moreover, a light output of higher luminance, high conversion efficiency and the emission of blue, green and red light having high color purity are required under present circumstances in terms of applications such as a full-color display.


For example, Japanese Patent Application Laid-Open No. 2001-52868 discloses a diamine compound as a light-emitting material, but any emission of blue light with high color purity (chromaticity coordinates: $x, y=0.14-0.15, 0.09-0.10$) is not obtained. Japanese Patent Application Laid-Open No. H11-312587 discloses an example using a similar diamino backbone, but any emission of blue light with

high color purity is not obtained.

DISCLOSURE OF THE INVENTION

The present invention has been created to solve these problems of prior art, and it is an object of the present invention to provide an organic light-emitting device that exhibits the hue of light emission having extremely high purity and has a light output having high luminance and long life with a high degree of efficiency and further to provide an organic light-emitting device that is easily produced and can be prepared at a relatively low cost.

According to an aspect of the present invention, there is provided an organic light-emitting device comprising a pair of electrodes consisting of an anode and a cathode and an organic compound-containing layer sandwiched between the pair of electrodes, wherein at least one layer of said organic compound-containing layers contains at least one compound selected from the group consisting of compounds represented by general formula [1]:



wherein


Y_1 and Y_3 can be bonded to Y_2 and Y_4 respectively to form a ring, and X_1 and X_3 can be bonded to Y_1 and/or Y_2 and Y_3 and/or Y_4 respectively to form a ring;

5 X_1 , X_2 and X_3 are the same or different and are each independently a direct bond or a divalent group selected from the group consisting of alkylene, aralkylene, arylene, divalent heterocyclic, alkenylene, imino, $-\text{SiH}_2-$, silylene, carbonyl, ether
10 and thioether, each having no substituent or a substituent which can include a linking group consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;

Y_1 to Y_4 are the same or different and are each
15 independently a group selected from the group consisting of alkyl, aralkyl, aryl, heterocyclic, amino, silyl, alkylene, aralkylene, alkenylene, imino, $-\text{SiH}_2-$, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can
20 include a linking group consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;


R_1 to R_8 are the same or different and are each independently hydrogen, halogen or a group selected
25 from the group consisting of alkyl, aralkyl and aryl, each having no substituent or a substituent; and $m+n$ is an integer from 0 to 10, and

at least one compound selected from the group consisting of compounds represented by general formulas [2] to [6]:



[2]


- 5 wherein Ar₁ to Ar₃ are the same or different and are each independently hydrogen or a group selected from the group consisting of aryl, heterocyclic, alkyl and aralkyl, each having no substituent or a substituent; and R₉ to R₁₁ are the same or different and are
- 10 hydrogen, halogen, cyano, a substituted amino or a group selected from the group consisting of alkyl, aralkyl and amino, each having no substituent or a substituent, and;



[3]


- 15 wherein Ar₄ to Ar₇ are the same or different and are each independently a group selected from the group consisting of aryl and heterocyclic, each having no substituent or a substituent; and R₁₂ and R₁₃ are the
- 20 same or different and are hydrogen, halogen, cyano, a

substituted amino or a group selected from the group consisting of alkyl and aralkyl, each having no substituent or a substituent;



[4]


- 5 wherein Ar₈ to Ar₁₂ are the same or different and are each independently a group selected from the group consisting of aryl and heterocyclic, each having no substituent or a substituent; and R₁₄ is hydrogen, halogen, cyano, a substituted amino or a group
 10 selected from the group consisting of alkyl, aralkyl, aryl and heterocyclic, each having no substituent or a substituent;



[5]

- 15 wherein Ar₁₃ to Ar₁₆ are the same or different and are each independently a group selected from the group consisting of aryl and heterocyclic, each having no substituent or a substituent, and any one to three of

Ar₁₃ to Ar₁₆ can be hydrogen or a group selected from the group consisting of alkyl and aralkyl, each having no substituent or a substituent; and R₁₅ to R₁₈ are the same or different and are hydrogen, halogen, cyano, a substituted amino or a group selected from the group consisting of alkyl, aralkyl, aryl and heterocyclic, each having no substituent or a substituent;



[6]

wherein R₁₉ and R₂₀ are the same or different and are hydrogen or a group selected from the group consisting of alkyl, aralkyl and aryl, each having no substituent or a substituent; any pair of R₁₉ combined to their respective fluorene structures are the same or different to each other; any pair of R₂₀ combined to their respective fluorene structures are the same or different to each other; R₂₁ to R₂₄ are hydrogen, halogen, cyano, a substituted silyl or a group selected from the group consisting of alkyl, aralkyl and alkoxy, each having no substituent or a substituent; and p is an integer from 2 to 10.

In the organic light-emitting device of the present invention, the layer that contains the

compound represented by general formula [1] and the compound represented by any of general formulas [2] to [6] is preferably a light-emitting layer.

5 BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a sectional view illustrating one example of the organic light-emitting device according to the present invention;

10 Fig. 2 is a sectional view illustrating another example of the organic light-emitting device according to the present invention;

Fig. 3 is a sectional view illustrating another example of the organic light-emitting device according to the present invention;

15 Fig. 4 is a sectional view illustrating another example of the organic light-emitting device according to the present invention;

20 Fig. 5 is a sectional view illustrating another example of the organic light-emitting device according to the present invention; and

Fig. 6 is a sectional view illustrating another example of the organic light-emitting device according to the present invention.

25 BEST MODE FOR CARRYING OUT THE INVENTION

The present invention will now be described in detail.

The compounds represented by the above general formulas [1] to [6] of the present invention will be first described.

The compounds represented by the general
5 formulas [1] to [6] according to the present
invention can be used mainly as a material for an
organic light-emitting device. In the compound [1],
an emission spectrum having a narrower half-value
width, that is, the emission having better color
10 purity can be obtained by introducing a relatively
rigid structure such as a p-phenylene skeleton into a
main molecular chain. Moreover, as the Stokes shift
can be suppressed, it is also possible to suppress
the transfer of light-emitting wavelength and bring
15 the absorption to a longer wavelength side. When
used as a dopant material, it is also possible to use
a host material having an emission spectrum at a
relatively longer wavelength side. Each of the
compounds represented by the general formulas [1] to
20 [6] can be used for both purposes, a dopant material
and a host material, in a light-emitting layer, and a
device having high color purity, high luminous
efficiency and long life can be obtained. In
particular, use of the compound represented by the
25 general formula [1] as a dopant material in
combination with any compound represented by the
general formulas [2] to [6] that is a suitable host

material that easily causes energy transfer allows the emission with high color purity to be maintained and a device having better efficiency to be obtained. The concentration of the dopant relative to the host material is preferably 0.01 to 50% by weight, more preferably 0.5 to 10% by weight.

Specific examples of the substituents in the above general formulas [1] to [6] are shown below.

Examples of substituted or unsubstituted chain and cyclic alkyl groups include methyl, ethyl, n-propyl, n-butyl, n-hexyl, n-decyl, iso-propyl, iso-butyl, tert-butyl, tert-octyl, trifluoromethyl, cyclohexyl and cyclohexylmethyl, but not limited thereto.

Examples of substituted or unsubstituted aralkyl groups include benzyl and phenetyl, but not limited thereto.

Examples of substituted or unsubstituted aryl groups include phenyl, 4-methylphenyl, 4-methoxyphenyl, 4-ethylphenyl, 4-fluorophenyl, 3,5-dimethylphenyl, triphenylamino, biphenyl, terphenyl, naphthyl, anthracenyl, phenanthrenyl, pyrenyl, tetracenyl, pentacenyl, fluorenyl, triphenylenyl and perylenyl, but not limited thereto.

Examples of substituted or unsubstituted heterocyclic groups include pyrrolyl, pyridyl, bipyridyl, methylpyridyl, terpyrrolyl, thienyl,

terthienyl, propylthienyl, furyl, quinolyl, carbazolyl, oxazolyl, oxadiazolyl, thiazolyl and thiadiazolyl, but not limited thereto.

5 Examples of substituted or unsubstituted alkylene groups include methylene, ethylene, propylene, iso-propylene, butylene, tert-butylene, hexylene, heptylene, cyclohexylene and cyclohexylmethylene, but not limited thereto.

10 Examples of substituted or unsubstituted aralkylene groups include benzylene, phenylethylene and phenethylene, but not limited thereto.

15 Examples of substituted or unsubstituted arylene groups include phenylene, biphenylene, 2,3,5,6-tetrafluorophenylene, 2,5-dimethylphenylene, naphthylene, anthracenylene, phenanthrenylene, tetracenylene, pentacenylene and perylenylene, but not limited thereto.

20 Examples of substituted or unsubstituted divalent heterocyclic groups include furanylene, pyrrolylene, pyridinylene, terpyridinylene, thiophenylene, terthiophenylene, oxazolylene, thiazolylene and carbazolylene, but not limited thereto.

25 Examples of substituted or unsubstituted alkenyl groups include vinyl, allyl (2-propenyl), 1-propenyl, iso-propenyl and 2-butenyl, but not limited thereto.

Examples of substituted or unsubstituted amino groups include amino, methylamino, ethylamino, dimethylamino, diethylamino, methylethylamino, benzylamino, methylbenzylamino, dibenzylamino, 5 anilino, diphenylamino, phenyltolylamino, ditolylamino and dianisolylamino, but not limited thereto.

Examples of substituted or unsubstituted carbonyl groups include acetyl, propionyl, isobutyl, 10 methacryloyl, benzoyl, naphthoyl, anthrayl and toluoyl, but not limited thereto.

Examples of substituted or unsubstituted alkoxy groups include methoxy, ethoxy, propoxy, 2-ethyl- 15 octyloxy, phenoxy, 4-butylphenoxy and benzyloxy, but not limited thereto.

Examples of substituted or unsubstituted sulfide groups include methylsulfide, ethylsulfide, phenylsulfide and 4-methylphenylsulfide, but not limited thereto.

20 Examples of substituents that may be owned by the above substituents include alkyl groups such as methyl, ethyl, n-propyl, iso-propyl, tert-butyl, octyl, benzyl, phenethyl and the like; alkoxy groups such as aralkyl, methoxy, ethoxy, propoxy, 2-ethyl- 25 octyloxy, phenoxy, 4-butylphenoxy, benzyloxy groups and the like; aryl groups such as phenyl, 4-methylphenyl, 4-ethylphenyl, 3-chlorophenyl, 3,5-

dimethylphenyl, triphenylamino, biphenyl, terphenyl,
 naphthyl, anthryl, phenanthryl and pyrenyl;
 heterocyclic groups such as pyridyl, bipyridyl,
 methylpyridyl, thienyl, terthienyl, propylthienyl,
 5 furyl, quinolyl, carbazolyl and N-ethylcarbazolyl;
 halogen, cyano and nitro, but not limited thereto.

The compounds shown by general formulas [1] to
 [6] are exemplified by compounds shown by the
 following formulae [1]-1 to [1]-91, [2]-1 to [2]-15,
 10 [3]-1 to [3]-14, [4]-1 to [4]-21, [5]-1 to [5]-14,
 and [6]-1 to [6]-7, respectively, but limited to them.




Table 1



































































[1]	m,n	R1 — R4	R5 — R8	X1	X2	X3	Y1	Y2	Y3	Y4
1	0,0	—	—	Single bond		Single bond	Ph	Ph	Ph	Ph
2	0,0	—	—	Single bond		Single bond				
3	0,0	—	—	Single bond		Single bond	Ph		Ph	
4	0,0	—	—	Single bond		Single bond	Ph		Ph	
5	0,0	—	—	Single bond		Single bond	Ph		Ph	
6	0,0	—	—	Single bond		Single bond	Ph		Ph	
7	0,0	—	—	Single bond		Single bond				
8	0,0	—	—	Single bond		Single bond	Ph		Ph	
9	0,0	—	—	Single bond		Single bond				
10	0,0	—	—	Single bond		Single bond	Ph		Ph	
11	0,0	—	—	Single bond		Single bond				
12	0,0	—	—	Single bond		Single bond	Ph		Ph	
13	0,0	—	—	Single bond		Single bond				
14	0,0	—	—	Single bond		Single bond	Ph		Ph	
15	0,0	—	—	Single bond		Single bond				
16	0,0	—	—	Single bond		Single bond				
17	0,0	—	—			Single bond				

Table 2

[1]	m,n	R1 — R4	R5 — R8	X1	X2	X3	Y1	Y2	Y3	Y4
18	0,0	—	—							
19	2,0	H	—	Single bond	Single bond	Single bond				
20	2,0	H	—	Single bond	Single bond	Single bond				
21	2,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
22	2,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
23	2,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
24	2,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
25	2,0	F	—	Single bond	Single bond	Single bond				
26	2,0	F	—	Single bond	Single bond	Single bond	Ph		Ph	
27	3,0	H	—	Single bond	Single bond	Single bond				
28	3,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
29	3,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
30	3,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
31	3,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
32	3,0	F	—	Single bond	Single bond	Single bond				
33	3,0	F	—	Single bond	Single bond	Single bond	Ph		Ph	
34	4,0	H	—	Single bond	Single bond	Single bond				
35	4,0	H	—	Single bond	Single bond	Single bond				
36	4,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	

Table 3


























































[1]	m,n	R1 — R4	R5 — R8	X1	X2	X3	Y1	Y2	Y3	Y4
37	4,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
38	4,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
39	4,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
40	4,0	H	—	Single bond	Single bond	Single bond				
41	4,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
42	4,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
43	4,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
44	4,0	F	—	Single bond	Single bond	Single bond				
45	4,0	F	—	Single bond	Single bond	Single bond	Ph		Ph	
46	5,0	H	—	Single bond	Single bond	Single bond				
47	5,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
48	5,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
49	5	H	—	Single bond	Single bond	Single bond	Ph		Ph	
50	5	H	—	Single bond	Single bond	Single bond	Ph		Ph	
51	5,0	H	—	Single bond	Single bond	Single bond				
52	5,0	H	—	Single bond	Single bond	Single bond	Ph		Ph	
53	1,1	H	F	Single bond	Single bond	Single bond				
54	2,1	H	F	Single bond	Single bond	Single bond				
55	2,2	H	F	Single bond	Single bond	Single bond				
56	1,1	H	H	Single bond		Single bond				

Table 4



























































































[1]	m,n	R1 — R4	R5 — R8	X1	X2	X3	Y1	Y2	Y3	Y4
57	1,1	H	H	Single bond		Single bond				
58	1,1	H	H	Single bond		Single bond	Ph		Ph	
59	1,1	H	H	Single bond		Single bond				
60	1,1	H	H	Single bond		Single bond				
61	1,1	H	H	Single bond		Single bond				
62	1,1	H	H	Single bond		Single bond				
63	1,1	H	H	Single bond		Single bond				
64	1,1	H	H	Single bond		Single bond				
65	1,1	H	H	Single bond		Single bond	Ph		Ph	
66	1,1	H	H	Single bond		Single bond	Ph		Ph	
67	1,1	H	H	Single bond		Single bond	Ph		Ph	
68	1,1	H	H	Single bond		Single bond				
69	1,1	H	H	Single bond		Single bond				
70	1,1	H	H	Single bond		Single bond				
71	1,1	H	H	Single bond		Single bond				
72	1,1	H	H	Single bond		Single bond				





Table 5


[1]	m,n	R1 — R4	R5 — R8	X1	X2	X3	Y1	Y2	Y3	Y4
73	1,1	H	H	Single bond		Single bond				
74	1,1	H	H	Single bond		Single bond				
75	2,2	H	H	Single bond		Single bond				
76	2,2	H	H	Single bond		Single bond				
77	2,2	H	H	Single bond		Single bond				
78	2,2	H	H	Single bond		Single bond				
79	1,1	H	F	Single bond		Single bond				
80	1,1	H	F	Single bond		Single bond				
81	1,1	H	F	Single bond		Single bond				
82	1,1	H	F		Single bond					
83	2,1	H	F		Single bond					
84	2,2	H	F		Single bond					
85	1,1	H	H							
86	2,2	H	H							














[3]-1








[3]-2









[3]-3




[3]-4









[4]




[4]-1





[4]-2




[4]-3




[4]-4







[4]-7




[4]-8




[4]-9




[4]-10




[4]-11




[4]-12




[4]-13




[4]-14




[4]-15




[4]-16




[4]-17




[4]-18




[4]-19







[4]-20











[4]-21




[5]










[5]-12




[5]-13




[5]-14




[6]-1




[6]-2




[6]-3




[6]-4



[6]-5



[6]-6



[6]-7

Figs. 1 to 6 illustrate preferred examples of the organic light-emitting devices of the present invention.

5 The example of Fig. 1 shows one example having a structure in which an anode 2, a light-emitting layer 3 and a cathode 4 are provided on substrate 1 in this order. The light-emitting device of this example is useful when it possesses a hole-transporting capability, an electron-transporting capability and light-emitting performance singly by
10 itself, or when compounds possessing them respectively are mixed for use.

 The example of Fig. 2 has the structure in which an anode 2, a hole-transporting layer 5, an
15 electron-transporting layer 6 and a cathode 4 are provided on substrate 1 in this order. This example is useful when a material having a hole-transporting capability and/or an electron-transporting capability is used for their respective layers and a light-
20 emitting substance in combination with a mere hole-transporting substance or an electron-transporting substance having no light-emitting property. In this case, the light-emitting layer is comprised of hole-transporting layer 5 or electron-transporting layer 6.

25 The example of Fig. 3 has the structure in which an anode 2, a hole-transporting layer 5 , a light-emitting layer 3, an electron-transporting

layer 6 and a cathode 4 are provided on a substrate 1 in this order, a carrier-transporting function and a light-emitting function being separated. The separation of the light-emitting layer from the charge-transporting layers extremely increases the freedom of material selection since compounds having a hole-transporting property, an electron-transporting property or a light-emitting property can be used in a suitable combination. For example, various compounds having different light-emitting wavelengths can be used to allow diversification of the hue of light emission. Further, it is also possible to try to improve the efficiency of light emission by effectively confining each carrier or exciton in the central light-emitting layer 3.

The example of Fig. 4 has the structure in which a hole-injecting layer 7 is arranged between anode 2 and hole-transporting layer 5 in the form of Fig. 3, which is effective in improving adhesiveness of anode 2 to hole-transporting layer 5, improving a hole-injecting property, being effective to reduce voltage.

Examples of Figs. 5 and 6 have the structure in which a layer for blocking a hole or an exciton from passing through to the side of the cathode 4 (hole-blocking layer 8) is inserted between light-emitting layer 3 and electron-transporting layer 6 in the

forms of Figs. 3 and 4. The use of a compound having a very high ionization potential as the hole-blocking layer 8 is an effective for improving the efficiency of light-emission in the structure.

5 Examples shown in Figs. 1 to 6 are very basic device structures, and the structures of the organic light-emitting device using the compounds of the present invention are not limited to them. It is possible to take various laminated structure, for
10 example, to provide an insulating layer to an interface between an electrode and an organic layer, to provide an adhesion layer or an interference layer or to compose the hole-transporting layer from two layers having different ionization potentials.

15 The compounds represented by general formulas [1] to [6] for use in the present invention can be used in any forms in Figs. 1 to 6.





 In particular, the organic layer using the compounds of the present invention is useful as a
20 light-emitting layer, an electron-transporting layer or a hole-transporting layer. In addition, the layer formed by a vacuum deposition process or a solution coating process hardly causes crystallization or the like and is excellent in the stability with time.

25 Although the present invention uses the compounds represented by the general formulas [1] to [6] as constituent components especially for the





light-emitting layer, already known hole-transporting compounds, light-emitting compounds or electron-transporting compounds can also be used together as necessary.

- 5 Examples of these compounds include the followings:


Hole-transporting compounds




M : Cu, Mg, AlCl, TiO, SiCl₂, Zn, Sn,
MnCl, GaCl, etc




Electron-transporting light-emitting materials




M : Al , Ga




M : Al , Ga




M : Zn , Mg , Be





M : Zn , Mg , Be




M : Zn , Mg , Be



M : Zn , Mg , Be










M : Zn , Mg , Be




M : Al , Ga


Light-emitting materials




Light-emitting layer matrix materials and electron-transporting materials



Polymer-based hole-transporting



Polymer-based light-emitting materials and
charge-transporting materials



In the organic light-emitting device of the
 5 present invention, the layers containing the
 compounds represented by the general formulas [1] to
 [6] and the layers comprising other organic compounds
 are generally formed into thin films by a vacuum
 deposition process or a coating process in which they
 10 are dissolved in a suitable solvent. In particular,
 when the film is formed by the coating process, it is

also possible to form the film in combination with suitable binding resins.

The above described binding resins can be selected from a wide range of binding resins, and include, but not limited to, polyvinylcarbazole resins, polycarbonate resins, polyester resins, polyallylate resins, polystyrene resins, acrylic resins, methacrylic resins, butyral resins, polyvinylacetal resins, diallylphthalate resins, phenol resins, epoxy resins, silicone resins, polysulfone resins, urea resins and the like. In addition, one of them or a mixture of two or more of them may be used in the form of a homopolymer or a copolymer.

The materials for the anode preferably have a large work function, and elemental metals such as gold, platinum, nickel, palladium, cobalt, serene, vanadium and alloys thereof and metal oxides such as tin oxides, zinc oxides, indium tin oxides (ITO) and indium zinc oxides can be used. In addition, conductive polymers such as polyaniline, polypyrrole, polythiophene and poyphenylene sulfide can be used. These electrode materials can be used singly or in combination.

The materials for the cathode preferably have a small work function, and elemental metals such as lithium, sodium, potassium, calcium, magnesium,

aluminum, indium, silver, lead, tin and chrome and alloys thereof can be used. Metal oxides such as indium tin oxides (ITO) can also be used. Moreover, the cathode may have one-layered structure or may
5 have a multilayered structure.

The substrates for use in the present invention include, but not limited to, metal substrates, opaque substrates such as ceramic substrates, transparent substrates such as glass, quartz and plastic sheet.
10 Moreover, it is possible to control the color of emitted light using a color filter film, a fluorescent color conversion filter film, a dielectric reflecting film and the like for the substrate.

15 Furthermore, a protective layer or a sealing layer can also be provided to the prepared device for the purpose of preventing contact with oxygen, moisture and the like. The protective layer includes an inorganic material film such as a diamond thin
20 film, a metal oxide or a metal nitride; a polymeric film such as a fluororesin, polyparaxylene, polyethylene, a silicone resin and a polystyrene resin; a photo-curable resin or the like. Moreover, the device itself can be covered with glass, a gas-
25 impermeable film, metal or the like and packaged with a suitable sealing resin.

Examples


The present invention will now be described in detail with reference to examples, but the present invention is not limited to them.

<Example 1>

5 An organic light-emitting device having the structure shown in Fig. 3 was prepared in a method illustrated below.

 On a glass substrate as substrate 1, indium tin oxide (ITO) of 120 nm in thickness as anode 2 was
10 deposited by a sputtering process and ultrasonically cleaned with acetone and isopropyl alcohol (IPA) in this order, and dried by boiling with IPA after the cleaning. Further, it was cleaned with UV/ozone. The resultant structure is referred to a transparent
15 conductive supporting substrate.

 There was prepared a 0.5% by weight chloroform solution of the compound represented by the following structural formula:



The solution was dropped on the ITO electrode (anode 2) of the transparent conductive supporting substrate, and was subjected to a spin coating first at a revolution of 500 RPM for 10 seconds and then at a revolution of 1,000 RPM for one minute to form a film. It was dried in a vacuum oven at 80°C for 10 minutes to completely remove the solvent in the thin film. The formed TPD film (hole-transporting layer 5) had a thickness of 50 nm.

On hole-transporting layer 5 the above illustrated compound No.[1]-6 and the above illustrated compound No.[2]-1 (weight ratio of 5:100) were subjected to co-deposition to provide light-emitting layer 3 of 20 nm. As for the conditions, the degree of vacuum at the deposition was 1.0×10^{-4} Pa and the speed of deposition was 0.2 to 0.3 nm/sec. Moreover, aluminum-quinolinol (Alq3) was deposited by a vacuum deposition process in a thickness of 40 nm to form electron-transporting layer 6. As for the conditions for depositing these organic layers, the degree of vacuum at the deposition was 1.0×10^{-4} Pa and the speed of deposition was 0.2 to 0.3 nm/sec.

Next, a vapor deposition material comprised of an aluminum-lithium alloy (lithium concentration of 1 atomic %) was used to form a metal layer film having a thickness of 10 nm on electron-transporting layer 6 by a vacuum deposition process, and further by the

vacuum deposition process an aluminum layer having a thickness of 150 nm was provided to form an electron-injecting electrode (cathode 4). As for the conditions, the degree of vacuum at the vapor
5 deposition was 1.0×10^{-4} Pa and the speed of deposition was 1.0 to 1.2 nm/sec.

The resultant structure was covered with a protective glass plate and sealed with an acrylic resin-based adhesive material in a dry air atmosphere
10 to prevent the degradation of the device due to moisture absorption.

When the thus obtained organic EL device was applied with a direct-current voltage of 9 V using an ITO electrode (anode 2) as a positive electrode and
15 an Al-Li electrode (cathode 4) as a negative electrode, the emission of blue light having an emission luminance of $1,250 \text{ cd/m}^2$, a maximum luminance of $3,770 \text{ cd/m}^2$ and a luminous efficiency of 0.45 lm/W was observed.

20 <Examples 2 to 7>

Devices were prepared and evaluated in the same manner as in Example 1 except that illustrated compounds shown in Table 6 replaced the illustrated compound [1]-6. The results are shown in Table 6.

Table 6

Example	Illustrated compound No.	Applied voltage (V)	Luminance (cd/m ²)	Maximum luminance (cd/m ²)	Efficiency (lm/W)
2	[1]-34	9	1670	5200	0.60
3	[1]-41	8	1840	6150	0.65
4	[1]-46	9	1730	5480	0.60
5	[1]-57	9	2050	6990	0.67
6	[1]-64	8	2200	7270	0.72
7	[1]-66	8	2600	7700	0.85

<Example 8>

A device was prepared in the same manner as in
 Example 1 except that the above illustrated compound
 No.[1]-41 and the above illustrated compound No.[2]-
 15 (weight ratio of 5:100) replaced the above
 illustrated compound No.[1]-6 and the above
 illustrated compound No.[2]-1 respectively to be
 subjected to the co-deposition to provide light-
 emitting layer 3 of 20 nm.

When the obtained device was applied with a
 direct-current voltage of 9 V using an ITO electrode
 (anode 2) as a positive electrode and an Al-Li
 electrode (cathode 4) as a negative electrode, the
 emission of blue light having an emission luminance
 of 1,680 cd/m², a maximum luminance of 4,650 cd/m² and
 a luminous efficiency of 0.57 lm/W was observed.

<Example 9>

A device was prepared in the same manner as in

Example 8 except that the illustrated compound No.[1]-57 replaced the illustrated compound No.[1]-41.

When the obtained device was applied with a direct-current voltage of 9 V using an ITO electrode (anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the emission of blue light having an emission luminance of 1,850 cd/m^2 , a maximum luminance of 4,950 cd/m^2 and a luminous efficiency of 0.58 lm/W was observed.

10 <Example 10>

A device was prepared in the same manner as in Example 1 except that the above illustrated compound No.[1]-41 and the above illustrated compound No.[3]-1 (weight ratio of 5:100) replaced the above illustrated compound No.[1]-6 and the above illustrated compound No.[2]-1 respectively to be subjected to the co-deposition to provide light-emitting layer 3 of 20 nm.

20 When the obtained device was applied with a direct-current voltage of 8 V using an ITO electrode (anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the emission of blue light having an emission luminance of 2,150 cd/m^2 , a maximum luminance of 6,840 cd/m^2 and a luminous efficiency of 0.71 lm/W was observed.

25

<Example 11>

A device was prepared in the same manner as in

Example 10 except that the illustrated compound No.[1]-39 replaced the illustrated compound No.[1]-41.

When the obtained device was applied with a direct-current voltage of 8 V using an ITO electrode (anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the emission of blue light having an emission luminance of 2,370 cd/m², a maximum luminance of 7,320 cd/m² and a luminous efficiency of 0.73 lm/W was observed.

<Example 12>

A device was prepared in the same manner as in Example 1 except that the above illustrated compound No.[1]-46 and the above illustrated compound No.[4]-1 (weight ratio of 5:100) replaced the above illustrated compound No.[1]-6 and the above illustrated compound No.[2]-1 respectively to be subjected to the co-deposition to provide light-emitting layer 3 of 20 nm.

When the obtained device was applied with a direct-current voltage of 8 V using an ITO electrode (anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the emission of blue light having an emission luminance of 2,200 cd/m², a maximum luminance of 6,760 cd/m² and a luminous efficiency of 0.72 lm/W was observed.

<Example 13>

A device was prepared in the same manner as in

Example 1 except that the above illustrated compound No.[1]-41 and the above illustrated compound No.[5]-2 (weight ratio of 5:100) replaced the above illustrated compound No.[1]-6 and the above
5 illustrated compound No.[2]-1 respectively to be subjected to the co-deposition to provide light-emitting layer 3 of 20 nm.

When the obtained device was applied with a direct-current voltage of 8 V using an ITO electrode
10 (anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the emission of blue light having an emission luminance of 3,100 cd/m², a maximum luminance of 7,250 cd/m² and a luminous efficiency of 1.02 lm/W was observed.

15 <Example 14>

A device was prepared in the same manner as in Example 1 except that the above illustrated compound No.[1]-39 and the above illustrated compound No.[5]-9 (weight ratio of 5:100) replaced the above
20 illustrated compound No.[1]-6 and the above illustrated compound No.[2]-1 respectively to be subjected to the co-deposition to provide light-emitting layer 3 of 20 nm.

When the obtained device was applied with a
25 direct-current voltage of 8 V using an ITO electrode (anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the

emission of blue light having an emission luminance of 4,500 cd/m², a maximum luminance of 8,420 cd/m² and a luminous efficiency of 1.18 lm/W was observed.

<Example 15>

5 A device was prepared in the same manner as in Example 1 except that the above illustrated compound No.[1]-57 and the above illustrated compound No.[6]-1 (weight ratio of 5:100) replaced the above
10 illustrated compound No.[1]-6 and the above illustrated compound No.[2]-1 respectively to be subjected to the co-deposition to provide light-emitting layer 3 of 20 nm.

 When the obtained device was applied with a direct-current voltage of 9 V using an ITO electrode
15 (anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the emission of blue light having an emission luminance of 1,980 cd/m², a maximum luminance of 5,300 cd/m² and a luminous efficiency of 0.60 lm/W was observed.

20 <Examples 16 to 21>

 The emission spectra of the devices prepared according to Examples 2, 5, 10, 12, 14 and 15 were observed with the MCPD-7000 and the CIE chromaticity coordinates were determined. The results are shown
25 in Table 7.

Table 7


Example	Example for device	CIE color coordinates (x, y)
16	2	0.15, 0.07
17	5	0.15, 0.10
18	10	0.15, 0.09
19	12	0.15, 0.10
20	14	0.16, 0.11
21	18	0.15, 0.10

<Example 22>

When the voltage was applied to the device prepared in Example 13 for 100 hours while maintaining the current density at 7.0 mA/cm² in a nitrogen atmosphere, the initial luminance of 480 cd/m² dropped to 410 cd/m² after 100 hours, exhibiting only a small reduction of luminance.

<Comparative Example 1>

A device was prepared in the same manner as in Example 1 except that, as light-emitting layer 3, there was used the following styryl compound:



When the obtained device was applied with a direct-current voltage of 10 V using an ITO electrode

(anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the emission of greenish blue white light having an emission luminance of 120 cd/m^2 , a maximum luminance of 3,800 cd/m^2 and a luminous efficiency of 0.17 lm/W was observed.

<Comparative Example 2>

A device was prepared in the same manner as in Example 1 except that the styryl compound in Comparative Example 1 and the above illustrated compound No.[4]-1 (weight ratio of 5:100) replaced the above illustrated compound No.[1]-6 and the above illustrated compound No.[2]-1 respectively to be subjected to the co-deposition to provide light-emitting layer 3 of 20 nm.

When the obtained device was applied with a direct-current voltage of 10 V using an ITO electrode (anode 2) as a positive electrode and an Al-Li electrode (cathode 4) as a negative electrode, the emission of greenish blue/white light having an emission luminance of 125 cd/m^2 , a maximum luminance of 4,500 cd/m^2 and a luminous efficiency of 0.30 lm/W was observed.

<Comparative Example 3>

The emission spectrum of the device prepared according to Comparative Example 2 was observed with the MCPD-7000 and the CIE chromaticity coordinates


were determined to be $(x, y) = (0.16, 0.30)$.

As described above by illustrating embodiments and examples, the organic light-emitting devices of the present invention provide the emission having
5 high luminance at a low applied voltage and are also excellent in color purity and durability, as a single layer or a mixed layer of a dopant/host by combining any of [2] to [6] with [1]. Moreover, it is possible to prepare the devices by using a vacuum deposition
10 process, casting process or the like, and the devices having a large area can be prepared easily at a relatively low cost.

CLAIMS

1. An organic light-emitting device comprising a pair of electrodes consisting of an anode and a cathode and an organic compound-containing layer sandwiched between the pair of electrodes, wherein at least one layer of the organic compound-containing layers contains

at least one compound selected from the group consisting of compounds represented by general formula [1]:



wherein

Y_1 and Y_3 can be bonded to Y_2 and Y_4 respectively to form a ring, and X_1 and X_3 can be bonded to Y_1 and/or Y_2 and Y_3 and/or Y_4 respectively to form a ring;

X_1 , X_2 and X_3 are the same or different and are each independently a direct bond or a divalent group selected from the group consisting of alkylene, aralkylene, arylene, divalent heterocyclic, alkenylene, imino, $-\text{SiH}_2-$, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group


consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;

Y₁ to Y₄ are the same or different and are each independently a group selected from the group
 5 consisting of alkyl, aralkyl, aryl, heterocyclic, amino, silyl, alkylene, aralkylene, alkenylene, imino, -SiH₂-, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group consisting of arylene or
 10 divalent heterocyclic, each having no substituent or a substituent;

R₁ to R₈ are the same or different and are each independently hydrogen, halogen or a group selected from the group consisting of alkyl, aralkyl and aryl,
 15 each having no substituent or a substituent; and

m+n is an integer from 0 to 10, and

at least one compound selected from the group consisting of compounds represented by general formula [2]:



[2]


20

wherein Ar₁ to Ar₃ are the same or different and are each independently hydrogen or a group selected from the group consisting of aryl, heterocyclic, alkyl and

aralkyl, each having no substituent or a substituent;
 and R_9 to R_{11} are the same or different and are
 hydrogen, halogen, cyano, a substituted amino or a
 group selected from the group consisting of alkyl,
 5 aralkyl and amino, each having no substituent or a
 substituent.

2. An organic light-emitting device comprising
 a pair of electrodes consisting of an anode and a
 10 cathode and an organic compound-containing layers
 sandwiched between the pair of electrodes, wherein at
 least one layer of the organic compound-containing
 layers contains

at least one compound selected from the group
 15 consisting of compounds represented by general
 formula [1]:



wherein

20 Y_1 and Y_3 can be bonded to Y_2 and Y_4 respectively
 to form a ring, and X_1 and X_3 can be bonded to Y_1
 and/or Y_2 and Y_3 and/or Y_4 respectively to form a
 ring;


X_1 , X_2 and X_3 are the same or different and are

each independently a direct bond or a divalent group selected from the group consisting of alkylene, aralkylene, arylene, divalent heterocyclic, alkenylene, imino, $-\text{SiH}_2-$, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;

Y_1 to Y_4 are the same or different and are each independently a group selected from the group consisting of alkyl, aralkyl, aryl, heterocyclic, amino, silyl, alkylene, aralkylene, alkenylene, imino, $-\text{SiH}_2-$, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;

R_1 to R_8 are the same or different and are each independently hydrogen, halogen or a group selected from the group consisting of alkyl, aralkyl and aryl, each having no substituent or a substituent; and $m+n$ is an integer from 0 to 10, and

at least one compound selected from the group consisting of compounds represented by general formula [3]:




[3]

wherein Ar₄ to Ar₇ are the same or different and are each independently a group selected from the group consisting of aryl, and heterocyclic, each having no substituent or a substituent; and R₁₂ and R₁₃ are the same or different and are hydrogen, halogen, cyano, a substituted amino or a group selected from the group consisting of alkyl and aralkyl, each having no substituent or a substituent.

3. An organic light-emitting device comprising a pair of electrodes consisting of an anode and a cathode and an organic compound-containing layer sandwiched between the pair of electrodes, wherein at least one layer of the organic compound-containing layers contains

at least one compound selected from the group consisting of compounds represented by general formula [1]:



wherein

Y₁ and Y₃ can be bonded to Y₂ and Y₄ respectively
5 to form a ring, and X₁ and X₃ can be bonded to Y₁
and/or Y₂ and Y₃ and/or Y₄ respectively to form a
ring;


X₁, X₂ and X₃ are the same or different and are each independently a direct bond or a divalent group selected from the group consisting of alkylene, 10 aralkylene, arylene, divalent heterocyclic, alkenylene, imino, -SiH₂-, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group 15 consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;

Y₁ to Y₄ are the same or different and are each independently a group selected from the group consisting of alkyl, aralkyl, aryl, heterocyclic, amino, silyl, alkylene, aralkylene, alkenylene, imino, -SiH₂-, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group consisting of arylene or

divalent heterocyclic, each having no substituent or a substituent;

R_1 to R_8 are the same or different and are each independently hydrogen, halogen or a group selected from the group consisting of alkyl, aralkyl and aryl, each having no substituent or a substituent; and $m+n$ is an integer from 0 to 10, and

at least one compound selected from the group consisting of compounds represented by general formula [4]:




[4]

wherein Ar_8 to Ar_{12} are the same or different and are each independently a group selected from the group consisting of aryl and heterocyclic, each having no substituent or a substituent; and R_{14} is hydrogen, halogen, cyano, a substituted amino or a group selected from the group consisting of alkyl, aralkyl, aryl and heterocyclic, each having no substituent or a substituent.

4. An organic light-emitting device comprising a pair of electrodes consisting of an anode and a

cathode and an organic compound-containing layers sandwiched between the pair of electrodes, wherein at least one layer of the organic compound-containing layers contains

- 5 at least one compound selected from the group consisting of compounds represented by general formula [1]:



- 10 wherein


Y_1 and Y_3 can be bonded to Y_2 and Y_4 respectively to form a ring, and X_1 and X_3 can be bonded to Y_1 and/or Y_2 and Y_3 and/or Y_4 respectively to form a ring;

- 15 X_1 , X_2 and X_3 are the same or different and are each independently a direct bond or a divalent group selected from the group consisting of alkylene, aralkylene, arylene, divalent heterocyclic, alkenylene, imino, $-\text{SiH}_2-$, silylene, carbonyl, ether
20 and thioether, each having no substituent or a substituent which can include a linking group consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;

Y₁ to Y₄ are the same or different and are each independently a group selected from the group consisting of alkyl, aralkyl, aryl, heterocyclic, amino, silyl, alkylene, aralkylene, alkenylene, imino, -SiH₂-, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;

R₁ to R₈ are the same or different and are each independently hydrogen, halogen or a group selected from the group consisting of alkyl, aralkyl and aryl, each having no substituent or a substituent; and m+n is an integer from 0 to 10, and

at least one compound selected from the group consisting of compounds represented by the following general formula [5]:




[5]

wherein Ar₁₃ to Ar₁₆ are the same or different and are each independently a group selected from the group consisting of aryl and heterocyclic, each having no

substituent or a substituent, and any one to three of Ar₁₃ to Ar₁₆ can be hydrogen or a group selected from the group consisting of alkyl and aralkyl, each having no substituent or a substituent; and R₁₅ to R₁₈ are the same or different and are hydrogen, halogen, cyano, a substituted amino or a group selected from the group consisting of alkyl, aralkyl, aryl and heterocyclic, each having no substituent or a substituent.

5. An organic light-emitting device comprising a pair of electrodes consisting of an anode and a cathode and an organic compound-containing layer sandwiched between the pair of electrodes, wherein at least one layer of the organic compound-containing layers contains

at least one compound selected from the group consisting of compounds represented by the following general formula [1]:



wherein

Y₁ and Y₃ can be bonded to Y₂ and Y₄ respectively to form a ring, and X₁ and X₃ can be bonded to Y₁

and/or Y_2 and Y_3 and/or Y_4 respectively to form a ring;


X_1 , X_2 and X_3 are the same or different and are each independently a direct bond or a divalent group selected from the group consisting of alkylene,
5 aralkylene, arylene, divalent heterocyclic, alkenylene, imino, $-\text{SiH}_2-$, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group
10 consisting of arylene or divalent heterocyclic, each having no substituent or a substituent;

Y_1 to Y_4 are the same or different and are each independently a group selected from the group consisting of alkyl, aralkyl, aryl, heterocyclic,
15 amino, silyl, alkylene, aralkylene, alkenylene, imino, $-\text{SiH}_2-$, silylene, carbonyl, ether and thioether, each having no substituent or a substituent which can include a linking group consisting of arylene or divalent heterocyclic, each having no substituent or
20 a substituent;

R_1 to R_8 are the same or different and are each independently hydrogen, halogen or a group selected from the group consisting of alkyl, aralkyl and aryl, each having no substituent or a substituent; and
25 $m+n$ is an integer from 0 to 10, and

at least one compound selected from the group consisting of compounds represented by the following

general formula [6]:



wherein R₁₉ and R₂₀ are the same or different and are
 5 hydrogen or a group selected from the group
 consisting of a alkyl, aralkyl and aryl, each having
 no substituent or a substituent; any pair of R₁₉
 combined to their respective fluorene structures are
 the same or different to each other; any pair of R₂₀
 10 combined to their respective fluorene structures are
 the same or different to each other; R₂₁ to R₂₄ are
 hydrogen, halogen, cyano, a substituted silyl or a
 group selected from the group consisting of alkyl,
 aralkyl and alkoxy, each having no substituent or a
 15 substituent; and p is an integer from 2 to 10.

6. The organic light-emitting device according
 to claim 1, wherein the layer containing the
 compounds represented by general formulas [1] and [2]
 20 is a light-emitting layer.

7. The organic light-emitting device according
 to claim 2, wherein the layer containing the

compounds represented by general formulas [1] and [3]
is a light-emitting layer.

5 8. The organic light-emitting device according
to claim 3, wherein the layer containing the
compounds represented by general formulas [1] and [4]
is a light-emitting layer.

10 9. The organic light-emitting device according
to claim 4, wherein the layer containing the
compounds represented by general formulas [1] and [5]
is a light-emitting layer.

15 10. The organic light-emitting device according
to claim 5, wherein the layer containing the
compounds represented by general formulas [1] and [6]
is a light-emitting layer.

ABSTRACT

To provide an organic light-emitting device that exhibits the hue of light emission having extremely high purity and has a light output having high luminance and long life with a high degree of efficiency.

The organic light-emitting device comprises at least a pair of electrodes consisting of an anode and a cathode and one or more organic compound-containing layers sandwiched between the pair of electrodes, wherein at least one of the above described organic compound-containing layers contains at least one compound selected from the group consisting of the compounds represented by the following general formula [1] and at least one compound selected from the group consisting of the compounds represented by the following general formula [2].




FIG. 1




FIG. 2




FIG. 3




FIG. 4






FIG. 5*FIG. 6*

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.